

LISTONE GIORDANO CLASSICA

High-end two-layers engineered hardwood floor with a top layer and crossed-fibres birch plywood support.

SPECIFICATIONS

PRODUCT	WIDTH	LENGTH**	TOTAL THICKNESS	TOP LAYER	SUPPORT	INSTALLATION SYSTEMS
Plank 230	230 mm	from 1500 to 2400 mm	14,0 mm	5,0 mm	multilayer birch plywood	glued
Plank 190	190 mm	from 1500 to 2400 mm	14,0 mm	5,0 mm	multilayer birch plywood	glued
Plank 140	140 mm	from 1200 to 2100 mm	14,0 mm	5,0 mm	multilayer birch plywood	glued
Listone 190	190 mm	from 1500 to 2400 mm	12,5 mm	3,5 mm	multilayer birch plywood	glued
Listone 140	140 mm	from 1200 to 2100 mm	12,5 mm	3,5 mm	multilayer birch plywood	glued
Prima 190	190 mm	from 1500 to 2400 mm	10,0 mm	2,5 mm	multilayer birch plywood	glued
Prima 140	140 mm	from 1500 to 1800 mm	10,0 mm	2,5 mm	multilayer birch plywood	glued
Prima 140 smart	140 mm	from 800 to 1200 mm	10,0 mm	2,5 mm	multilayer birch plywood	glued
Prima flottante 190	190 mm	1800 mm	14,0 mm	2,5 mm	multilayer spruce plywood	floating/nailed/ glued*
Prima flottante 140 smart	140 mm	1200 mm	14,0 mm	2,5 mm	multilayer spruce plywood	floating/nailed/ glued*
Listone 90	90 mm	from 490 to 1200 mm	11,0 mm	3,5 mm	multilayer birch plywood	glued
Corona 70	70 mm	from 350 to 600 mm	9 mm	3,5 mm	multilayer birch plywood	glued

* Due to lower thickness and minor thermal resistance, Prima 140 and 190 are more suitable for glue-down installation, especially on underfloor heating systems.

** The products are supplied in one length or random lengths, according to availability.

The material supplied may incorporate up to 10% of shorter lengths compared to those mentioned in the specifications

OTHER TECHNICAL INFORMATION

TOP-SUPPORT LAYER GLUING	<p>Conforms to the requirements of the <i>class D4 of the UNI EN 204 regulation</i></p> <p>Conforms to the requirements of the <i>JAS type II norm</i></p> <p>(cycle made of 2h in hot water at 70°C and then immediately 3h in an airy stove at 60°C)</p>
PROFILE	<p>Interlocking tongues and grooves on 4 sides</p> <p>Plank and Listone 140 and 190 versions are available both bevelled on all 4 edges and with sharp edges.</p> <p>Prima 140 and 190 and Prima flottante 140 and 190 versions are available only bevelled on all 4 edges.</p> <p>Listone 90 and Corona 70 versions are available only with sharp edges.</p>

WOOD SPECIES

WOOD SPECIES	NATURAL VEGETATION AREA	HARDNESS
Oak	European forests	high
Canadian Maple	Canada, Eastern United States and the great lakes region	medium/high
Cabreuva	Paraguay, Brazil and Argentina outside amazon forest	very high
American Black Walnut	Junglas nigra – north America	high
Iroko	Mid-western equatorial zone of the African continent	medium/high
Teak	Southern Asia and the Indian peninsula	high
Wenge	Central-south eastern African equatorial band	very high
Cherry	European forests	medium/high
Doussié	Equatorial band in the central-western area of the African continent	very high
Jatoba	Tropical-equatorial zone that goes from Bolivia to Mexico	very high
Morado	South American forests, especially in Brazil and Bolivia	very high

To verify the availability of the various versions of Listone Giordano® products, consult the current Price list.

FINISH

Listone Giordano® Classica is available with the following finishes.

XPLUS2

Acrylic, U.V. cured, 100% dry residue (solvent free) varnish are applied; these varnishes are specifically designed to obtain the best results in terms of resistance to wear (more than 30.000 Taber rotations - test performed by CS10 grindstone, abrasion until the wood is exposed), elasticity of the varnish, adherence to the wood and transparency.

XPlus22 finish has a smooth surface, sleek satin appearance with a fully compact pore and a surface reflectance of approximately 18 gloss.

NATURPLUS 2

Acrylic, U.V. cured, 100% dry residue (solvent free) varnishes are applied; these varnishes are specifically designed to obtain excellent results in terms of resistance to surface abrasion (more than 10.000 Taber rotations - test performed by CS10 grindstone, abrasion until the wood is exposed), elasticity of the varnish, adherence to the wood and transparency.

NaturPlus2 finish is only available with a brushed finish: a special treatment is performed on the wood's surface before the varnish is applied in order to accentuate the appearance of the wood's natural pores and fibres.

The surface reflectance of the NaturPlus2 finish has a value of approximately 7 gloss.

INVISIBLE TOUCH

Water-based finish, has the characteristic of protecting the wood whilst maintaining the typical appearance and colour of an untreated hardwood floor.

The specific application technique open pore allows the varnish offering a natural appearance, both visual and tactile.

OLEONATURE

Air-dried natural oils-based finish. The oils-based finish incorporates colour pigments in some products such as Oak "Michelangelo". Before finishing is applied, some wood species undergo a brushing treatment, to remove the soft parts, highlighting the wood pores and fibres. Thanks to the industrially applied final protective coating, the Oleonature finish ensures easy maintenance compared to other oil finishes and better resistance against household liquids' penetration.

Products with natural oil finishing tend to get a yellowish colour tone, should these products be kept, for instance, in the boxes for a longtime or not being exposed to light and air. It's an utterly natural and transitory phenomenon.

This effect is reversible within a few days and the wood can restore its original appearance, once the boards are exposed to air and direct sunlight whilst in an environment with artificial light it may take up to few weeks.

Listone Giordano® Classica Oak is also available in the **Pre-sanded** version with a surface ready to be finished on site after the installation.

Oak wood species is available both in the natural version (Puro) and in the various colours of the Michelangelo version: Biancospino, Carvi, Tamarindo, Tortora, Testa di Moro, Shetland, Cemento, Creta, Cashmere, Lino, Montblanc, Bianco Assoluto.

Wood is a natural material, therefore colour tone and absorption of the finish may vary from one board to the other, or even in the same board according to the variation of its fibre. These colour tone variation is visible even after the application of colour pigments proving the authenticity and the uniqueness of each board.

All the above mentioned finishing are complying with antibacterial Crystalcare technology.

GRADES

Listone Giordano® Classica is available with the following grades.

RIGATA SUPERIORE

Straight grain, light colour and substantially homogenous, presence of medullary ray on the majority of the wooden boards.

ELITE

Mixed grain, substantially homogeneous colour in relation to the typical characteristics of the species.
Possible small knots in some woods species.

FIBRAMIX

Mixed grain. Some boards may show colour variations and knots.
In the extra-wide boards (from 140 mm width) knots may be even tight and open.

UNICA

Mixed grain and colour variation. Presence of knots both filled and open ones. Some wood boards may show sapwood according to the different wood species.

COUNTRY

Mixed grain and colour variation. Widespread presence of knots both tight and open ones.

DIRECTIONS FOR LAYING

INTERIOR CONDITIONS

Before the installation make sure that all work on site (decoration, installation of sanitary fixtures, etc.) has been completed. Maintain the humidity level between 45% and 65% and the temperature between 16 and 25°C because outside of these ranges the boards may suffer deformation and adhesives and other products used for the installation may not work correctly.

SUBFLOOR CHECK

The subfloor on which the hardwood flooring is to be installed must be smooth, level, and have a compact surface so as to guarantee the best possible contact between the underside of the planks and the subfloor itself.

Carry out the following checks before installation:

- **Smoothness/Flatness of the subfloor:** a 2 metre long straight edge should be placed on the subfloor, the maximum allowable tolerance is 2-3 mm.
- **Concrete subfloor superficial structural strength:** when hammering the surface no marks or deep cracking should appear.
- **Concrete subfloor superficial compactness control:** it should not be possible to create deep scratches or excessive dust when scrapping the surface of the subfloor with a nail.
- **Fissuring:** small fissures created as a result of the normal shrinkage of the cement are allowable, but excessive cracks, in particular those which permeate throughout the complete thickness of the subfloor, must be properly consolidated by suitable and permanent means.
- **Cleaning:** before the installation begins it is very important to carefully clean and check the surface of the subfloor.
- **Moisture content:** the moisture content of the subfloor has to be within the recommended limits for the specific type of subfloor. The subfloor residual moisture control has to be executed only using calcium carbide hygrometer (other tools could give wrong measurements in certain conditions) and the maximum values allowed for the installation are:
 - 2,0% for a concrete slab (max. thickness 80 mm);
 - 0,4% for anhydride slab;
 - 10,0% for wooden panels.

In case of thick subfloor this control has to be done on the total thickness, not only on the surface.

In case of installation on underfloor heating system the maximum values allowed are lower (see paragraph "Installation on underfloor radiating system" below).

Should these requirements not be fulfilled, implement proper operation before installation.

The laying of Listone Giordano® can also be carried out on pre-existing flooring, provided that they are checked all the conditions of flatness, solidity, compactness, cleaning of the surface, absence of cracks and of residual moisture or lift necessary to ensure proper contact at every point of the surface and the protection from external side. For installation over existing hard flooring (ceramic, stone, etc.), should in particular ensure that the surface is likely to ensure proper bonding. Where necessary action must be taken with a preliminary treatment of deep cleaning, degreasing, scratch the surface by mechanical means and/or suitable chemicals.

The glued installation is not compatible with pre-existing type textile floor coverings (i.e carpets) or resilient (linoleum, pvc, etc.), which must therefore necessarily be removed.

MATERIAL STORAGE

We recommend the boxes of hardwood flooring are stored in secure, dry and weather proof rooms and not placed directly on the ground. Open the boxes only as the flooring is being installed and no more than what is needed.

INSTALLATION SYSTEMS

In the table at page 1 allowed installation systems for each product are indicated.

Please follow directions below according to the installation system.

GLUE DOWN INSTALLATION

Choose an adhesive that is compatible with the characteristics of the sub-floor and that won't transmit humidity to the wood (do not use adhesives that contain water).

Ecolfit® Listone Giordano® is the one component adhesive recommended for all the range of our hardwood floors.

The glue is to be applied homogeneously onto the whole subfloor surface (do not apply it on individual strip/board or discontinuously). Do not apply the glue directly underneath the boards.

Spread the adhesive on the subfloor only using a suitably notched trowel and lay the boards on top by interlocking them, if possible, using only a little pressure.
 The boards have to be joined only by hands avoiding the use of other tools (for instance the mallets) that can create damages on the surface and the corners of the boards.
 During this operation take care not to allow adhesive into the joints or on the surface.

It's forbidden the use of Pulplus® Listone Giordano or aggressive solvents to remove adhesive residues on oil finished hardwood floor especially if stained.

Around the entire perimeter of the interiors, including the point of junction with thresholds of other flooring materials, it is compulsory to form an expansion joint amplitude of about 10 mm to be filled with appropriate skirting along the vertical walls and thresholds in connection with other joints in the floors.

FLOATING INSTALLATION

In case of floating installation, if there is any evidence of, or even doubt about, the possibility of moisture intrusion (for example on ground floors or on subfloors recently built or containing high humidity lightening materials, etc.) it is necessary to lay a double polyethylene sheet over the subfloor and extend it a few centimetres up the walls to form an effective moisture barrier.

Before starting the actual installation of the planks, it is essential to lay foam underlay that will provide sound insulation.

The installation of the boards is carried out by inserting a continuous bead of glue (suitable for floating hardwood floors) on the upper part of the groove.

It is necessary to take care, when laying the floor, that end joints in one row are not lined up with end joints in adjacent rows; the correct staggering can be obtained by choosing an appropriate length for the first plank in a row.

All around the perimeter of the room, including where the hardwood floor meets other flooring materials, it is essential to leave an expansion gap of about 10 mm (more if the room is particularly large) that will be covered by a suitable skirting board along the walls or by a threshold where the wood floor meets a different floor surface or a door.

It is necessary to allow for intermediary dilatation gaps every 6/8 metres, both width-wise and length-wise.

During installation, any adhesive that accidentally comes into contact with the top surface of the planks should be wiped away quickly with a damp cloth. If the adhesive is allowed to dry on the surface, its removal will require considerable effort risking to alter the shining of the hardwood floor.

INSTALLATION ON UNDERFLOOR RADIATING SYSTEM

When the glue down installation is over an underfloor heating system, it is necessary first of all check that:

- the distance between the wood and the heating pipes or cables embedded in the screed is at no point less than 30 mm;
- the heating system is one that functions at a low temperature
- the system is provided of proper regulation tools in order to avoid that **the contact temperature of the hardwood floor surface will exceed 27°C.**

Should these indications not be fully complied the floor could suffer not only dimensional deformations and gapping between the boards but also permanent damages.

The construction characteristics of the sub-floor have a greater importance in case of installation on underfloor radiating system; particularly **the maximum residual humidity that cannot be more than 1.7% CM.**

The glue down installation on an area with an underfloor heating system is strongly advisable to reach best performances both regarding the best conduction of heat into the rooms and because it confers greater dimensional stability on the planks (the variation of interior conditions creates minor deformations).

The thermal resistance values (the lower the thermal resistance, the better is the heating conduction) are reported in the table below:

PRODUCT	TOTAL THICKNESS	THERMAL RESISTANCE R [m² K / W]*
Plank 140 , 190 and 230	14,0 mm	0,086

Listone 190 and 140	12,5 mm	0,077
Prima 140, 140 smart and 190	10,0 mm	0,062
Prima flottante 140 and 190	14,0 mm	0,104
Listone 90	11,0 mm	0,067
Corona 70	9,5 mm	0,058

*approximate values related to the oak top layer version.

With a floating installation it would be necessary to add the thermal resistance of the sound insulation foam underlay and particularly that of the air in any empty spaces that might remain under the flooring. Thermal resistance can increase so much.

For any further information about installation see the sheets PO 1 - Listone Giordano® over underfloor heating system.

ADDITIONAL TREATMENTS. SIGILPLUS

The Sigilplus® treatment has been created for hardwood floors with *XPlus2 and NaturPlus2* finish for protecting and water-proofing the boards.

This treatment is **compulsory** in each room for Steamed Beech Canadian Maple hardwood floors and it is strongly recommended on all types of wood in rooms with a higher incidence of fallings or leakages of liquids (bath-rooms and kitchens).

Only for NaturPlus2 finish treat the floorboards before they are installed by applying the product directly onto the sides of the boards using a small paintbrush.

For any proper information more see information sheet PM 6 – Sigilplus.

AFTER THE INSTALLATION

At the end of the laying remove the dirt and dust found on the floor's surface by cleaning with a vacuum cleaner equipped with a brush suitable for hardwood floors.

For *Oleonature and Invisible Touch* finish wash the floor with Green Listone Giordano® diluting half a cup (approximately 100 ml) of product in a 5 l bucket of water.

INSTRUCTIONS FOR USE

Maintain the humidity level of the atmosphere between 45% and 65% and the temperature between 15 and 30°C. This is also the same environmental conditions recommended for ensuring people's comfort and health.

The use of humidifiers or dehumidifiers is highly recommended in order to keep the above mentioned conditions.

Temperature or air humidity level not complying to the conditions above may cause deformations, cracks and sometimes permanent damages of the hardwood floor.

Use protective felt pads for furniture, chair legs, etc.

Any armchair on castors should be covered with suitable rubber.

We recommend the use of a proper door-mat to clean the shoes.

Rugs and carpets should be removed from time to time especially soon after hardwood floor installation in order to avoid creating areas with different colour tone according to the natural oxidisation of the wood.

Objects with weight concentrated over small surface areas cause localised indentations in the surface of the wood.

Rubber shoes soles leave dirty marks on the surface which could prove hard to remove.

Not to use sticky tape and adhesives materials on the surface because, in case of remaining for a prolonged time or with high temperature, they can leave marks difficult to remove.

A slight darkening effect can appear in time in the deeper parts of the wood (brushings, sawings, etc.) due to the accumulation of the dust. Regular maintenance of the floor will reduce this appearance.

CLEANING AND MAINTENANCE

Never wash the floor with tap water only: it will not efficiently clean the surface of the floor and, moreover, the minerals contained in water may leave behind a residue that could affect the surface appearance of the floor.

Do not use liquids containing acid or basic concentrations, such as bleach or ammonia, which could create marks/halos on the wood that would be impossible to remove.

For proper cleaning and maintenance we advise to only use products recommended by ourselves for the various finishes as indicated in the following table:

FINISH	CLEANING	ORDINARY MAINTENANCE	PROFESSIONAL USE
XPlus2	Green	Vitaplus	Extraclean
NaturPlus2	Green	Vitaplus	Extraclean
Invisible Touch	Green	Vitanova	/
Oleonature	Green	Revivo	/

You can find below directions for use of each product.

EXTRACLEAN

(Aggressive detergent suitable to remove resistant dirt on XPlus2 and NaturPlus2 hardwood floors)

Shake well. Water down the Extraclean Listone Giordano® at the 50% or, for tough dirt, 66% (2 parts of Extraclean and 1 of water).

Poor onto the floor and wipe by a cotton cloth.

This operation can be done also by a single-brush buffer machine fitted with a white pad and a soft cotton cloth.

After the application you will have a liquid contaminated with the dirt that you will have to remove very carefully avoiding that it remains on the floor (dry this liquid by means of soft cotton cloths or extractor liquids fan).

Leave the floor dry not using any product nor buffing.

In case of need repeat the cleaning operations.

The daily use of Extraclean Listone Giordano® may cause the surface to become more opaque over a shorter period of time.

A 1 litre bottle of Extraclean Listone Giordano® diluted with water is generally sufficient for treating a surface area of approximately 40–50 m².

GREEN

(Mild detergent for the cleaning of XPlus2, NaturPlus2, Oleonature and Invisible Touch finished hardwood floors)

Remove the dust found on the floor’s surface by cleaning with a vacuum cleaner equipped with a brush suitable for hardwood floors.

Shake well.

Dilute half a cup of Green Listone Giordano® (100 ml approximately) in a 5 l bucket of water.

Immerse a lint free soft cotton rag in the solution, wring well and pass it over the floor’s surface using a long-handled floor brush/mop. Use a cloth that will not leave fibre residues.

No need to rinse.

In case of tough dirt wash the floor with Green Listone Giordano® in double dose.

Never exceed this concentration and don’t use often this detergent in double dose: it may cause older appearance of the surface over a shorter period of time.

Do not repeat often this operation because the surface could appear less consistent.

1 litre of product is sufficient for washing approximately 10 times a surface area of 100 m².

VITAPLUS

(Protective and renovating product for XPlus2 and NaturPlus2 finished hardwood floors)

Vitaplus® Listone Giordano is a protective and renovating liquid: its regular use creates a surface film that slows natural wear caused by foot traffic and restores the varnish’s transparency and shine.

Remove all dirt and impurities from the hardwood floor’s surface using a vacuum cleaner.

Shake well; pour a small amount of Vitaplus® Listone Giordano solution pure directly onto the floor.

Distribute evenly and rub the surface lightly with a soft cloth.

It is important that only a thin layer of product be applied to ensure the proper execution of the steps to follow in the treatment process.

After max 15 minutes from the application, homogenize and polish with a domestic floor buffing machine equipped with felt pads (do not use bristle brushes), or mop with a soft rag pushed along by a long-handled floor brush.

Wait 1 hour from when the solution is applied before step on the floor.

Vitaplus® also cleans the surfaces it is applied to; therefore, the rubbing action removes the traces of dirt (especially grease, oil, etc.) that were not removed during vacuum cleaning.

A 1 litre bottle of Vitaplus® treats a surface area of approximately 50-60 m².

The use of Vitaplus® Listone Giordano must be scheduled based on the intensity of the floor's use and looking at its appearance; it is estimated that it must be applied every 1-2 years.

Be certain to follow the necessary precautions for inflammable products when using Vitaplus®.

VITANOVA

(Protective and renovating product for Invisible Touch finished hardwood floors)

Vitanova is a protective and renovating liquid: its regular use slows natural wear caused by foot traffic and restores an homogeneous appearance on the surface.

Before applying it, thoroughly clean the surface of the floor using Green Listone Giordano® in double dose according to the instructions above. Always use Vitanova Listone Giordano® at temperatures above +15°C.

Shake very well.

Wait the floor will be well dry.

Spread a thin and homogeneous layer of the product according to the wood grain. Use a soft lint free cotton cloth that will not leave fibre residues underneath a long-handled floor brush or by hand.

In case of brushed or open pore floors we recommend to apply a limited quantity of Vitanova Listone Giordano® because it could permeate the brushings or the pores making it difficult to be removed.

Once the product is applied, the floor's surface should have a slightly wet appearance.

After 1-2 hours the floor is dry and can be walked upon.

The application of Vitanova Listone Giordano® helps to homogenize the floor; no other application is therefore required.

1 litre of product is sufficient for spreading a coat on a surface area of approximately 30 m².

Use this product approximately every 6 months in the first year after the installation of the hardwood flooring and every 12 months from the second year on.

We recommend more frequent maintenance operations in case of average and heavy-duty traffic environments.

REVIVO

(Natural oil-wax product to nourish and protect Oleonature wood floors)

Revivo Listone Giordano® is a protective and renovating liquid: its regular use slows natural wear caused by foot traffic and restores an homogeneous appearance on the surface.

Before applying it, thoroughly clean the surface of the floor using Green Listone Giordano® in double dose according to the instructions above. Always use Revivo Listone Giordano® at temperatures above +15°C.

Shake very well.

Wait the floor will be well dry.

Spread a thin and homogeneous layer of the product according to the wood grain. Use a soft lint free cotton cloth that will not leave fibre residues underneath a long-handled floor brush or by hand.

In case of brushed or open pore floors we recommend to apply a limited quantity of Revivo Listone Giordano® because it could permeate the brushings or the pores making it difficult to be removed.

Once the product is applied, the floor's surface should have a slightly wet appearance.

After 1-2 hours the floor is dry and can be walked upon.

1 litre of product is sufficient for spreading a coat on a surface area of approximately 30 m².

Use this product approximately every 6 months in the first year after the installation of the hardwood flooring and every 12 months from the second year on.

We recommend more frequent maintenance operations in case of average and heavy-duty traffic environments.

GRADES CHARACTERISTICS

(according to the requirements of the european norm EN13489 – Multi-layer parquet elements – *Free class*)

CHARACTERISTIC	RIGATA SUPERIORE	ELITE	FIBRAMIX	UNICA	COUNTRY
Sound sapwood	Not permitted	Not permitted	Not permitted	Permitted	Not permitted
Knots (sound, intergrown and unsound)	Permitted if: Diameter < 1 mm	Permitted if: Diameter < 8 mm	Permitted if: Diameter < 12 mm	All permitted without limits	All permitted without limits
Yellow stain	Permitted	Permitted	Permitted	Permitted	Permitted
Checks	Not permitted	Not permitted	Not permitted	Not permitted	Not permitted
Bark pockets	Not permitted	Not permitted	Not permitted	Not permitted	Not permitted
Lightning shake	Not permitted	Not permitted	Not permitted	Not permitted	Not permitted
Curly grain	Not permitted	Permitted	Permitted	Permitted	Permitted
Slope of grain	Not permitted	Permitted without limit	Permitted without limit	Permitted without limit	Permitted without limit
Sound heart	Permitted	Permitted	Permitted	Permitted	Permitted
Colour variation (including blackheart, red heart, etc.)	Permitted	Permitted	Permitted	Permitted	Permitted
Stick marks	Not permitted	Not permitted	Not permitted	Not permitted	Not permitted
Medullary ray	Permitted	Permitted	Permitted	Permitted	Permitted
Biodeterioration	Not permitted	Not permitted	Not permitted	Not permitted	Not permitted

Non-visible parts: all features permitted without any limitation as to size or quantity if these do not impair the strength or wearing quality of the parquet flooring.

During the production and quality control processes all the above dimensions and characteristics are optically estimated from skilled operators, without using any measurement device.

For this reason allowance are permitted in the above dimensional data.

CERTIFICATIONS




BIOSPHERA

Biosphera is a marking system based upon Listone Giordano's green procurement policy to provide consumers with brief, clear and useful information on the origin of raw materials. Many products of the collection Listone Giordano® Classica offer both in their top layer and in their support the *Biosphera certified* mark that identifies raw materials whose forestry management is certified according to recognized standards at the international level (FSC, PEFC, SFI, OLB, LEI, etc.) or the *Biosphera controlled* mark that identifies raw materials whose legal sourcing and forestry management, although not yet certified, is backed up by specific audit and related papers. The full list of the products certified is available on the technical sheet EC 2 - Biosphera certifications on Listone Giordano® products.



MARCATURA CE

All the products of the collection Listone Giordano® Classica strictly comply to all CE rules regarding hardwood floors.



AIR EMISSIONS

Emissions of Volatile Organic Compounds All Listone Giordano products tested according to n°2011-321 French Decree have attained A+ rating, the highest among those in the decree.



SOLVENT FREE

No emission of solvents, as resulting from the analyses conducted on Listone Giordano® by the SERECO BIOTEST chemical laboratory.



FORMALDEHYDE

All the products of the collection Listone Giordano® Classica comply to the class E1, which is amongst the strictest European regulations (UNI EN 14342).



CARB Certification - ATCM 93120

The updated product's list incorporating plywood panels that complies to the CARB Phase 2 standard requirements regarding formaldehyde emissions is available on www.listonegiordano.com.



ANTI-BACTERIAL FINISH CRYSTALCARE

All the XPlus2, NaturPlus2, Invisible Touch and Oleonature finishes are antibacterial certified by CATAS S.p.a laboratories according to ISO 22196:2007 regulation.



DIBt

Certification of the construction products released from DIBt - Deutsches Institut für Bautechnik/German institute for civil engineering.



ISO 9001

Quality Management System certification.



ISO 14001

Environmental Management System certification for the Miralduolo di Torgiano (PG) factory

MADE IN

All the products of the collection Listone Giordano® Classica are Made in Italy.



FIRE REACTION CERTIFICATION

In the following table you can find fire reaction classes of the various products:

PRODUCT	FINISH	FIRE REACTION CLASS <small>(according to the requirements of the EN14342 regulation on the CE mark)</small>
Plank 140 , Plank 190 and Plank 230	XPlus2	Cfl-s1 (Oak,Cabreuva,Walnut,Morado) Other wood species: Dfl-s1
	NaturPlus2	Oak, Cfl-s1 Other wood species: Dfl-s1
	Invisible Touch	Oak: Cfl-s1 Other wood species: Dfl-s1
	Oleonature	Oak: Cfl-s1 On demand Walnut fireproof oil Cfl-s1 Other wood species: Dfl-s1
Listone 140 and Listone 190	XPlus2	Cfl-s1 (Oak,Cabreuva,Walnut,Morado) Other wood species: Dfl-s1
	NaturPlus2	Oak Cfl-s1 Other wood species: Dfl-s1
	Invisible Touch	Dfl-s1
	Oleonature	On demand Oak, Walnut: Cfl-s1 Other wood species: Dfl-s1
Prima 140, Prima 140 Smart and Prima 190	NaturPlus2	Oak, Walnut: Cfl-s1 Other wood species: Dfl-s1
	Invisible Touch	Dfl-s1
	Oleonature	On demand Oak, Walnut : Cfl-s1 Other wood species: Dfl-s1
Prima flottante 140 smart and Prima flottante 190	NaturPlus2	Oak: Cfl-s1 Other wood species: Dfl-s1
	Invisible Touch	Dfl-s1
	Oleonature	On demand Oak: Cfl-s1 Other wood species: Dfl-s1
Listone 90	XPlus2	Cfl-s1 (Oak,Cabreuva,Walnut,Morado) Other wood species: Dfl-s1
	NaturPlus2	Oak, Walnut: Cfl-s1 Other wood species: Dfl-s1
	Invisible Touch	Dfl-s1
	Oleonature	On demand Oak, Walnut: Cfl-s1 Other wood species: Dfl-s1
Corona 70	XPlus2	Cfl-s1 (Oak,Cabreuva,Walnut,Morado) Other wood species: Dfl-s1
	NaturPlus2	Oak, Doussié, Iroko: Cfl-s1 Other wood species: Dfl-s1
	Invisible Touch	Dfl-s1
	Oleonature	Dfl-s1

IMPORTANT INFORMATION ABOUT HARDWOOD FLOORS

WOOD AS A LIVING MATERIAL

Wood is a “living” material interacting with the environment therefore it is affected by exterior elements such as light, UV rays, temperature, humidity and daily use (wear and tear).

COLOUR

The colour of wood largely depends upon particular substances known as extractives which change due to the exposure to light. This results in alterations and more or less marked variations from the original color of every type of wood flooring.

Due to the higher extractives content in tropical wood species, these species are especially prone to chromatic changes usually evolving into a darker brown colour tone. Iroko and Doussié are two of the species that experience a stronger colour variation. Doussié especially may show localized effects of rapid and intense oxidation even on boards originally of the same colour tone.

Under specific conditions these alteration traces of mineral substances, where are a natural part of the wood structure, may become more evident.

Teak may initially show more evident colour variations. These variations tend to mitigate and homogenize to a middle-clear tones overtime.

Even Oak, however characterized by a good colour stability in relation with other wood species, is due to change overtime and tends to warmer colour tones, whilst intensifying the yellow hue. This phenomenon occurs even in colour- pigmented products (i.e. “Michelangelo” collection).

The long exposure of some wood species to intense and direct sunlight, such through window-panes, may cause discoloration (UV rays produce these effects on materials other than wood). In order to prevent this phenomenon, we recommend the use of curtains or special UV filtering films to be applied to the glass panes.

SAMPLES

Wood is a natural material, not characterized by uniformity-regularity: two elements of the same piece of timber will never have an identical aesthetic appearance. Therefore samples made of few wooden boards can only represent an illustration or general idea and cannot fully show the different tones, grains and uniqueness.

As mentioned above, wood is prone to alter its colour tone overtime, due to exposure to light and air. Therefore a recently installed wood floor may typically show a different aesthetic and colour tone compared to a sample panel of the same product which has been exposed to natural light for a period of time.

MEDULLARY RAYS (Silver Figures)

Strips from a perfect radial section of a log in some wood species (especially Oak and Beech), feature straight grains and typical silver figures, the so-called medullary ray (still evident in the colour finishes as well).

This type of graining is the result of the perfect radial cut of the log and enhances the quality and the value of the wood product. In addition to the better aesthetical appearance it's an indication of improved technical performance (regularity of the fiber, dimensional stability water proof, impermeability, etc.).

WEATHER CONDITIONS

Wood is naturally affected by dimensional variations due to humidity and temperature of the environment. **In order to avoid damages and unwanted effects, the climate conditions of the rooms should meet the following requirements: air temperature must remain between 15°C and 30°C and relative humidity must be between 45% and 65%.** These conditions provide as well a suitable and healthy environment to live in.

The prolonged exposure to a very dry atmospheric condition can lead even a modern and technologically advanced multilayer product to shrink and gaps to appear in between wood strips.

This phenomenon is reversible and gaps are due to close again once correct climate conditions are restored.

Extreme dryness or high humidity in the air may generate a certain level of stress and alterations in the wood structure, very high at times, in the worst cases this can create micro-fractures on the top hardwood layer (due to the sliding of the interface in

between growth rings consequential to the exceeding elastic limit). For these reasons it is compulsory that proper climate conditions are to be maintained both during the installation process and afterwards, even if the premises are unoccupied. **In some situations, particularly in the winter months to ensure compliance with the conditions mentioned above the use of an air humidifier may prove necessary.** **In the case of heated floors, in addition to the requirements relating to temperature and humidity of the air, the temperature's limit of the floor surface, when the system is in function, must not exceed 27°C.**

FRACTURES

The appearance overtime of micro-fractures on the top hardwood layer is a natural phenomenon and inevitable in statistic terms even if recommended climate conditions are to be maintained.

HARDNESS

The individual hardness of all wood species processed to manufacture products featured in this pricelist are suitable to become hardwood flooring. However surface indentations may arise in even the hardest of woods, if the hardwood floor is subjected to knocks, falling objects, in addition to highly concentrated weight (stiletto heels, ladder, etc.)

HANDCRAFTED WORKS

Atelier and Natural Genius wood flooring collections with crafted treatments feature non homogenous, dimensional and aesthetic characteristics typical of a hand-made product. Therefore prospective tolerances related to the planarity of the boards, or even within the individual boards (i.e. planarity, roughness or colour tone of the surface) are not to be considered by any means a defect but on the contrary the craftsmanship value of the products itself.

The distinctive crafted finishes can create some irregularity and splintering of the wood surface where cloth used for cleaning and maintenance may get trapped. These elements of irregularity and splintering are to be considered (taken into account) when walking bare feet on the floor.

VARNISHES

The wear and tear is prone to alter the shine level of the floor surfaces as time passes, especially in high-traffic areas. A correct maintenance can keep this phenomenon under control.

NATURAL OIL FINISHES

Products with natural oil finishing tend to get a yellowish colour tone, should these products be kept in the boxes for a longtime or not being exposed to light and air.

It's an utterly natural and transitory phenomenon. This effect is reversible within a few days, once the wood boards are exposed to direct sunlight whilst in an environment with artificial light it may take up to few weeks before restoring the original appearance.

The oils-based finishing has the characteristic to continue over time to permeate the wood fibers even while the material is still inside the packaging boxes. The possible appearance of surface dryness that you should notice on newly installed planks, will be restored with the application of the specific maintenance product after installation.

USE AND MAINTENANCE INSTRUCTIONS

Instructions of the correct use and maintenance of the wood flooring are available in the dedicated page of the website www.listonegiordano.com/international featuring the technical sheets.

We recommend checking it when selecting the product.